

# WATER-BASED RELEASE AGENT FOR CONCRETE FORMWORK

# DISCRETE EMULSION

## TECHNICAL DATA

### 1.0 DESCRIPTION

DISCRETE EMULSION is a stable, water-emulsion concrete release agent that reacts with the alkali content of concrete to form a bond-breaking film. It is VOC compliant, non-toxic and environmentally safe.

### 2.0 ADVANTAGES & BENEFITS

DISCRETE EMULSION:


- Water based, environmentally safe.
- Stable emulsion - doesn't require continual stirring.
- Is effective on all types of moulds and formwork.
- Increases the life of wood forms by impregnating the timber rendering it water-resistant and preventing deterioration.
- Can be applied to forms used in precast concrete manufacture.
- Will not stain or discolour concrete
- Can be used on plastic, rubber and other delicate formwork.

### 3.0 PHYSICAL PROPERTIES

3.1 Colour	Milky white
3.2 Specific Gravity	1.0
3.3 Flash Point	Not Combustible
3.4 Viscosity	Very low (Sprayable)
3.5 Toxicity	Non toxic
3.6 D.G. Classification	Not Regulated
3.7 Shelf Life	Unlimited in original sealed containers not exposed to frost or freezing.
3.8 Coverage	Timber Formwork (porous).....up to 19m <sup>2</sup> /litre Metal Formwork (dense)..... up to 40m <sup>2</sup> /litre Coverages are approximate only and will vary depending on porosity of surface.

### 4.0 USES

DISCRETE EMULSION is effective on all types of moulds and formwork, especially rubber and plastic (test on aluminium forms prior to use). It may be used for architectural and precast concrete as well as for general forming applications. DISCRETE EMULSION may be sprayed daily onto mixers, hoist buckets, wheelbarrows and all other equipment and machinery on which concrete may adhere to keep the concrete soft and easily removed. DISCRETE EMULSION is offers excellent abrasion resistance on rotating moulds.



## Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: [www.fbsltd.co.nz](http://www.fbsltd.co.nz)

Email: [info@fbsltd.co.nz](mailto:info@fbsltd.co.nz)

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



# DISCRETE EMULSION

---

## TECHNICAL DATA Continued

---

### 5.0 APPLICATION

- 5.1 Store away from frost and keep above 10°C where possible.
- 5.2 Application is preferably by spray (wide angle, low flow, flat spray nozzle) which will permit the rates of coverage to be obtained. Brush application may also be employed but the material should be well brushed out to obtain the most economic and effective results. Avoid puddles/ponding. Mop up any excess with a clean cloth or paper towel.
- 5.3 Being a chemical release agent, DISCRETE EMULSION does not rely for its effectiveness on quantity, and is still active although the formwork may appear dry. Do not over apply to new and porous wood.
- 5.4 Formwork is best treated before being erected, thus avoiding contamination of reinforcement. Should reinforcement become coated with DISCRETE EMULSION by accident, it should be painted with cement slurry to react with the DISCRETE EMULSION and this slurry should be brushed off immediately before the concrete is poured.
- 5.5 Once treated, formwork should be protected from precipitation and dust.
- 5.6 DISCRETE EMULSION should be applied to the formwork prior to each use.

### 6.0 PACKAGING

4, 20 and 210-litre containers.

Refer to Material Safety Data Sheet for handling and first aid information.



## **Fraser Brown & Stratmore Ltd**

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: [www.fbsltd.co.nz](http://www.fbsltd.co.nz)

Email: [info@fbsltd.co.nz](mailto:info@fbsltd.co.nz)

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.

