

FIBERCAST™ 500

PRODUCT DATA SHEET

FIBERCAST™ 500 SYNTHETIC FIBER

FiberCast 500, formerly Harbourite®, micro-reinforcement system for concrete—100 percent virgin homopolymer polypropylene fibers containing no reprocessed olefin materials. Specifically engineered and manufactured in an ISO 9001:2000 certified facility for use as concrete reinforcement for precast applications at a minimum of 0.1% by volume. UL Classified. Complies with National Building Codes and ASTM C III6 Type III 4.1.3., ASTM C III6 Performance Level I and Residual Strength.

ADVANTAGES

Accepted by National Codes as an alternate method of secondary reinforcing to traditional systems • Non-magnetic • Rustproof • Alkali proof • Requires no minimum amount of concrete cover • Is always positioned in compliance with codes • Safe and easy to use • Reduces construction time

FEATURES & BENEFITS

- Alternate construction system to traditional reinforcement commonly used for secondary (crack control) reinforcing in concrete.
- Inhibits and controls the formation of intrinsic cracking in concrete
- Reinforces against impact forces
- Reinforces against the effect of shattering forces
- Reinforces against material loss from abrading forces
- Reinforces against water migration
- Imparts toughness to hardened concrete
- Reduces plastic shrinkage and settlement cracking
- Provides residual strength
- Provides increased green strength

PRIMARY APPLICATIONS

Applicable to all types of concrete which demonstrate a need for toughness, resistance to intrinsic cracking and improved water tightness.

- Septic tanks
- Manhole cones and risers
- Statuaries
- Agricultural products
- Marine products
- Hazardous material storage
- Utility structures
- Burial vaults

CHEMICAL AND PHYSICAL PROPERTIES:

Absorption	Nil	Modulus (Young's)	0.5 (3.5 kN/mm ²)
Specific Gravity	0.91	Melt Point	324°F (162°C)
Fiber Length	.25 in - 2 in (6.35 mm - 50 mm)	Ignition Point	1,100°F (593°C)
Thermal Conductivity	Low	Electrical Conductivity	Low
Acid & Salt Resistance	High	Alkali Resistance	Alkali Proof

DO SPECIFY FIBERCAST 500 FIBERS:

- Reduced plastic shrinkage cracking
- Alternative to traditional reinforcement
- Improved impact, shatter and abrasion resistance
- Improved residual strength
- Reduced water migration and damage from freeze/thaw
- Improved durability
- Areas requiring non-metallic materials
- Improved green strength

DO NOT SPECIFY FIBERCAST 500 FIBERS:

- Crack control from external stresses
- Replacing any moment or structural steel



THE ADVANTAGE CREATORS.™

CONCRETE SYSTEMS

FIBERCAST™ 500

PRODUCT USE

MIXING DESIGNS AND PROCEDURES: Fibercast™ 500 micro reinforcing is a mechanical, not chemical, process. The addition of Fibercast 500 fiber does not require any additional water or other mix design changes at normal rates. Fibercast 500 fiber is added to the mixer before, during or after batching the other concrete materials. Mixing time and speed are specified in ASTM C 94.

FINISHING: Fibercast 500 micro-reinforced concrete can be finished by normal finishing techniques.

APPLICATION RATE: The standard application rate for Fibercast 500 fibers is 0.1% (minimum 1.5 lbs/yd³, 0.9 kg/m³) by volume. For specialty performance see your local Propex Concrete Systems representative for recommendations regarding increased application rates.

GUIDELINES

Fibercast 500 fibers should not be used to replace structural, load-bearing reinforcement. Fibercast 500 fibers should not be used as a means of using thinner concrete sections than original design.

COMPATIBILITY

Fibercast 500 fibers are compatible with all concrete admixtures and performance enhancing chemicals, but require no admixtures to work.

PACKAGING

Fibercast 500 fibers are available in a variety of packaging options. Special packaging is available for full truckload addition. Bags are packed into cartons, shrink-wrapped and palletized for protection during shipping.

TECHNICAL SERVICES

Trained Propex Concrete Systems specialists are available worldwide to assist and advise in specifications and field service. Propex Concrete Systems representatives do not engage in the practice of engineering or supervision of projects and are available solely for service and support of our customers.

SPECIFICATION CLAUSE

Use only 100 percent virgin polypropylene Fibercast 500 fibers containing no reprocessed olefin materials and specifically manufactured for use as concrete secondary reinforcement. Application rate per cubic yard shall equal a minimum of 0.1% (minimum 1.5 lbs/yd³, 0.9 kg/m³) by volume. Fibercast 500 fibers are for the control of cracking due to drying shrinkage and thermal expansion/contraction, lowered permeability, increased impact capacity, shatter resistance, abrasion resistance and residual strength. Fiber manufacturer must document evidence of 10 year satisfactory performance history, ISO 9001:2000 certification of manufacturing facility, compliance with applicable building codes and ASTM C III6 Type III, 4.1.3, ASTM C III6 (Ref: ASTM C 1018) Performance Level I, I5 outlined in Section 21, Note 17 and an average minimum Residual Strength of 50 psi, of 4 beams from a single batch. Fibrous concrete reinforcement shall be manufactured by Propex Concrete Systems, 6025 Lee Highway, Suite 425, PO Box 22788, Chattanooga, TN, 37422, USA, tel: 423 892 8080, fax: 423 892 0157, web site: fibermesh.com.



THE ADVANTAGE CREATORS.™

NORTH AMERICA

Propex Concrete Systems Corp.
6025 Lee Highway, Suite 425
PO Box 22788
Chattanooga, TN 37422
Tel: 800 621 1273
Tel: 423 892 8080
Fax: 423 892 0157

INTERNATIONAL

Propex Concrete Systems Ltd.
Propex House, 9 Royal Court, Basil Close
Chesterfield, Derbyshire, S41 7SL.UK
Tel: +44 (0) 1246 564200
Fax: +44 (0) 1246 465201

www.fibermesh.com

Fibermesh®, Novomesh®, Novocon®, ENDURO® and e3® are registered trademarks of Propex Concrete Systems Corp.

THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. **PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.**

CS-511
©2006 Propex Concrete Systems Corp.
07/06