

FIBERMESH® 150

PRODUCT DATA SHEET

FIBERMESH® 150 SYNTHETIC FIBER

Fibermesh 150, formerly Stealth® e3®, micro-reinforcement system for concrete—100 percent virgin homopolymer polypropylene multifilament fibers containing no reprocessed olefin materials. Specifically engineered and manufactured in an ISO 9001-2000 certified facility for use as concrete reinforcement at a minimum of 1.0 pound per cubic yard (.60 kg per cubic meter). UL Classified. Complies with National Building Codes and ASTM C 1116 Type III 4.1.3.

ADVANTAGES

Non-magnetic • Rustproof • Alkali proof • Requires no minimum amount of concrete cover • Is always positioned in compliance with codes • Safe and easy to use • Saves time and hassle.

FEATURES & BENEFITS

- Inhibits and controls the formation of intrinsic cracking in concrete
- Reinforces against impact forces
- Reinforces against abrasion
- Reinforces against the effect of shattering forces
- Reinforces against water migration
- Provides improved durability
- Reduces plastic shrinkage and settlement cracking
- Alternate system to traditional reinforcement when used for secondary (crack control) reinforcing in concrete

PRIMARY APPLICATIONS

Applicable to all types of concrete which demonstrate a need for resistance to intrinsic cracking and improved water tightness and an aesthetic finish.

- Slab-on-grade
- Stucco
- Slope paving
- Sidewalks
- Curbs
- Exposed aggregate
- Driveways
- Overlays/Toppings

CHEMICAL AND PHYSICAL PROPERTIES

Absorption	Nil	Melt Point	324°F (162°C)
Specific Gravity	0.91	Ignition Point	1100°F (593°C)
Fiber Length*	Graded	Thermal Conductivity	Low
Electrical Conductivity	Low	Alkali Resistance	Alkali Proof
Acid & Salt Resistance	High		

*Also available in single cut lengths

DO SPECIFY FIBERMESH 150 FIBERS:

- Reduced plastic shrinkage cracking
- Improved impact, shatter and abrasion resistance
- Reduced water migration and damage from freeze/thaw
- Improved durability
- Areas requiring non-metallic materials
- Concrete that needs an architectural finish

DO NOT SPECIFY FIBERMESH 150 FIBERS:

- Crack control from external stresses
- Increasing joint spacing beyond ACI and PCA guidelines
- Decreasing thickness of slabs
- Replacing any moment or structural steel



FIBERMESH® 150

PRODUCT USE

MIXING DESIGNS AND PROCEDURES: Fibermesh® 150 micro reinforcing is a mechanical, not chemical, process. The addition of Fibermesh 150 multifilament fibers do not require any additional water nor other mix design changes at normal rates. Fibermesh 150 fibers are added to the mixer before, during or after batching the other concrete materials. Mixing time and speed are specified in ASTM C 94.

FINISHING: Fibermesh 150 micro-reinforced concrete can be finished by any finishing technique. Exposed aggregate, broomed and tined surfaces are no problem.

APPLICATION RATE: The minimum application rate for Fibermesh 150 fibers is 1.0 pound per cubic yard (.60 kg/m³).

GUIDELINES

Fibermesh 150 fibers should not be used to replace structural, load bearing reinforcement. Fibermesh 150 fibers should not be used as a means of using thinner concrete sections than original design. Fibermesh 150 fibers should not be used to increase joint spacing past those dimensions suggested by PCA and ACI industry standard guidelines.

COMPATIBILITY

Fibermesh 150 fibers are compatible with all concrete admixtures and performance enhancing chemicals, but require no admixtures to work.

PACKAGING

Fibermesh 150 fibers are available in a variety of packaging options. Special packaging is available for full truckload addition. Fibermesh 150 fibers are packaged, packed into cartons, shrink wrapped and palletized for protection during shipping.

TECHNICAL SERVICES

Trained SI® Concrete Systems specialists are available worldwide to assist and advise in specifications and field service. SI Concrete Systems representatives do not engage in the practice of engineering or supervision of projects and are available solely for service and support of our customers.

REFERENCES

- ASTM C94 Standard Specification for Ready-Mixed Concrete Uniformity Requirements.
- ASTM C1399 Average Residual Strength of Fiber Reinforced Concrete.
- ASTM C1436 Standard Specification for Materials for Shotcrete.
- ASTM C1018 Standard Test Method for Flexural Toughness and First-Crack Strength of Fiber-Reinforced Concrete.
- ASTM C1116 Standard Specification for Fiber-Reinforced Concrete And Shotcrete.
- ACI 304 Guide for Measuring, Mixing, Transporting and Placing Concrete.
- ACI 506 Guide for Shotcrete.
- UL Approvals for use as an alternate or in addition to welded wire fabric used in floor-ceiling D700, D800 and D900 series designs.
- International Code Council (ICC) NER-414 Evaluation Report.

SPECIFICATION CLAUSE

Use Fibermesh 150 only 100 percent virgin polypropylene fibers containing no reprocessed olefin materials and specifically engineered and manufactured in an ISO 9001-2000 certified facility for use as concrete secondary reinforcement. Application per cubic yard shall equal a minimum of 1.0 pounds per cubic yard (.60 kg/m³). Fibers are for the control of cracking due to plastic shrinkage, plastic settlement and thermal expansion/contraction, lowered permeability, increased impact, abrasion and shatter resistance. Fiber manufacturer must document evidence of five-year satisfactory performance history, compliance with applicable building codes and ASTM C 1116 Type III, 4.1.3. Fibrous concrete reinforcement shall be manufactured by SI® Concrete Systems, 4019 Industry Drive, Chattanooga, Tennessee, USA, 37416. Phone: (423) 892-8080, Fax: (423) 892-0157, e-mail: fibermesh@sind.com.



For those who prefer performance to tradition.

USA
4019 Industry Drive
Chattanooga, Tennessee 37416
TEL: (423) 892-8080
FAX: (423) 892-0157

INTERNATIONAL
Hayfield House, Devonshire Street,
Chesterfield, Derbyshire, S41 7ST. UK
TEL: +44 (0) 1246 564200
FAX: +44 (0) 1246 564201

www.siconcretesystems.com

"Fibermesh®", "Novomesh®", "Novocon®", and "e3®" are registered trademarks of SI® Corporation.

Warranty and limitation of claims. This guide is intended solely for use by personnel who it is contemplated will evaluate the significance and limitations of the information provided herein ("information"). SI Corporation warrants that products which it manufactures that are described herein ("products") will be of marketable quality, free of any defect in material and workmanship. Because SI Corporation has no control over the design, manufacture, use or testing of the projects which incorporate the products, SI makes no warranty of results to be obtained. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. SI Corporation disclaims any and all responsibility and liability for the accuracy and the application of the information. The foregoing limited warranty is in lieu of and excludes all other warranties, whether express or implied, by operation of law or otherwise, including but not limited to, any implied warranties of merchantability or fitness for a particular purpose.

© SI Corporation, Inc. CS-509 01/05